

Quality Paints since 1845  
**MATHYS®**



**PEGALINK®**

## Universal adhesion primer

- Excellent adhesion on a lot of surfaces
- Flexible
- Excellent flow
- UV-resistant

# PEGALINK®

## DESCRIPTION

Universal adhesion primer based on water dispersed acrylic resins.

## RECOMMENDED USE

Adhesion on a lot of surfaces: wood, gypsum, cement, bricks and especially on smooth and difficult to adhere to surfaces like: galvanized steel, copper, zinc, polycarbonate, hard PVC, Pegagraff Hydro, etc. Can be used in- and outdoors.

## TECHNICAL DATA

Density (g/cm <sup>3</sup> ):	1,2 - 1,3
Gloss Level:	Satin
Gloss level at 60°:	Satin: ± 20%
Solids Content in weight:	± 52 %
Solids content in volume:	± 37 %

## DRY TIMES BY 20° C/RH 50%

Touch dry:	20 minutes
Dry to handle:	1 hour
Dry to recoat:	24 hours with waterborne paints. Decorative alkyd lacquers should be checked first by means of an adhesion test.
Fully cured:	2 days

## RECOMMENDED WET FILM THICKNESS

100 µm

## RECOMMENDED DRY FILM THICKNESS

36 µm

## THEORETICAL CONSUMPTION

± 10 m<sup>2</sup>/l

## PRACTICAL CONSUMPTION

Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application.

## SURFACE PREPARATION

In general, it is not necessary to mat smooth surfaces by sanding; in most cases cleaning and/or degreasing of the surface is sufficient in order to obtain good adhesion.

## DIRECTIONS FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

## APPLICATION CONDITIONS

> 5°C, < 80% R.H.

## APPLICATION & THINNING: BRUSH

All types can be used. Do not dilute.

## APPLICATION & THINNING: ROLLER

Not recommended, except with a lacquer roller. Do not dilute

## APPLICATION & THINNING: AIRLESS SPRAY

Nozzle: 11 / Pressure: 200 bars. Do not dilute.

## APPLICATION & THINNING: AIR-ATOMISED SPRAY

Possible, do not dilute.

## CLEANING OF EQUIPMENT / SPILLS

Water.

## REMARKS

Adhesion cross-cut intact on the above-mentioned surfaces.

In case of doubt, f.i. on a substrate which has not been mentioned, an adhesion test has to be done after 2 days of drying, especially on old paints.

## SAFETY DATA

VOC level:	45 g/l
VOC ready mix:	45 g/l
VOC category:	A/1
VOC limit:	140 g/l
Remarks regarding safety:	Consult Safety Data Sheet and Safety Information printed on the can.

## SHELF LIFE

Minimum of 2 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Date issued: 23/10/2023

**Available colours & pack sizes:** Please refer to the respective product page on [www.rust-oleum.eu](http://www.rust-oleum.eu) for an overview of actual available colours and pack sizes.

**Disclaimer:** The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Rust-Oleum Europe be liable for consequential or incidental damages. Products must be stored, handled, and applied under conditions complying with Rust-Oleum Europe recommendations detailed within the latest copy of the product data sheet. It is the users responsibility to ensure that they have the current copy. Latest copies of the product data sheet is available for free and downloadable from [www.rust-oleum.eu](http://www.rust-oleum.eu) or upon a request to our Customer Services department. Rust-Oleum Europe reserves the right to change the properties of its' products without prior notification.

**Rust-Oleum Netherlands B.V.**  
Zilverenberg 16  
5234 GM 's-Hertogenbosch  
The Netherlands  
T : +31 (0) 165 593 636  
F : +31 (0) 165 593 600  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Tor Coatings Ltd (Rust-Oleum Industrial)**  
Shadon Way, Portobello Ind. Estate  
Birtley, Chester-le-Street  
DH3 2RE United Kingdom  
T : +44 (0)1914 113 146  
F : +44 (0)1914 113 147  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**Rust-Oleum France S.A.S.**  
38, av. du Gros Chêne  
95322 Herblay  
France  
T : +33(0) 130 40 00 44  
F : +33(0) 130 40 99 80  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)

**N.V. Martin Mathys S.A.**  
Kolenbergstraat 23  
3545 Zelem  
Belgium  
T : +32 (0) 13 460 200  
F : +32 (0) 13 460 201  
[info@rust-oleum.eu](mailto:info@rust-oleum.eu)